

Figure 4™ Standalone

Affordable and compact industrial-grade solution for lower cost production parts



Figure 4 Standalone

Build Volume (xyz)	124.8 x 70.2 x 196 mm (4.9 x 2.8 x 7.7 in)
Max Resolution	1920 x 1080 pixels
Pixel Pitch	65 microns (0.0025 in) (390.8 effective PPI)
Wavelength	405 nm
Build Materials	UV curable plastics: Figure 4 TOUGH-GRY 10, Figure 4 TOUGH-GRY 15, Figure 4 ELAST-BLK 10, Figure 4 JCAST-GRN 10
Material Packaging	1kg bottles for manual pour
Operating Environment Temperature Humidity (RH)	18-28 °C (64-82 °F) 20-80%
Electrical	100-240 VAC, 50/60 Hz, Single Phase, 4.0A
Dimensions (WxDxH) 3D Printer crated Pedestal crated 3D Printer uncrated 3D Printer with Pedestal uncrated	73.66 x 68.58 x 129.54 cm (29 x 27 x 51 in) 82.55 x 79.375 x 55.245 cm (32.5 x 31.25 x 21.75 in) 42.6 x 48.9 x 97.1 cm (16.7 x 19.25 x 38.22 in) 68.1 x 70.4 x 135.6 cm (26.8 x 27.71 x 53.38 in)
Weight 3D Printer crated Pedestal crated 3D Printer uncrated 3D Printer with Pedestal uncrated	59 kg (130 lbs) 26.3 kg (58 lbs) 34.5 kg (76 lbs) 54.4 kg (120 lbs)
3D Sprint® Software	Easy build job set-up, submission and job queue management; Automatic part placement and build optimization tools; Part nesting capability; part editing tools; Automatic support generation; Job statistics
3D Connect™ Capable	3D Connect Service provides a secure cloud-based connection to 3D Systems service teams for proactive and preventative support. 3D Connect Manage helps customers manage and monitor equipment with anytime, anywhere access to print jobs, system performance metrics and usage.
Connectivity	10/100/1000 Ethernet Interface
Client Hardware Recommendation	<ul style="list-style-type: none"> • 3 GHz multiple core processor (2 GHz Intel® or AMD® processor mini) with 8 GB RAM or more (4 GB mini) • OpenGL 3.2 and GLSL 1.50 support (OpenGL 2.1 and GLSL 1.20 mini), 1 GB video RAM or more, 1280 x 1024 (1280 x 960 mini) screen resolution or higher • SSD or 10,000 RPM hard disk drive (minimum requirement of 7 GB of available hard-disk space, additional 3 GB free disk space for cache) • Google Chrome or Internet Explorer 11 (Internet Explorer 9 mini) • Other: 3 button mouse with scroll, keyboard, Microsoft .NET Framework 4.6.1 installed with application
Client Operating System	Windows® 7 and newer (64-bit OS)
Input Data File Formats Supported	STL, CTL, OBJ, PLY, ZPR, ZBD, AMF, WRL, 3DS, FBX, IGES, IGS, STEP, STP and X_T
Post-Processing	Includes part finishing tools accessory kit; Requires optional 3D Systems LC-3DPrint Box UV post-curing unit or other UV-curing unit
Accessories	LC-3DPrint Box UV post-curing unit (option, not included), Pedestal (included)
Certifications	FCC, CE, EMC

Note: Not all products and materials are available in all countries – please consult your local sales representative for availability

Figure 4™ Materials for Figure 4 Standalone

A variety of robust, production-grade materials

The production-grade materials available for Figure 4 Standalone include a broad and expanding range of industrial materials, including tough production, fast prototyping, cast and elastomeric materials.



Figure 4 TOUGH-GRY 10



Figure 4 TOUGH-GRY 15



Figure 4 ELAST-BLK 10



Figure 4 JCAST-GRN 10

Properties	Condition	Figure 4 TOUGH-GRY 10	Figure 4 TOUGH-GRY 15	Figure 4 ELAST-BLK 10	Figure 4 JCAST-GRN 10
Viscosity (cps)	at 25 °C	490	780	1200	190
Color		Dark Gray	Gray	Black	Green
Solid Density (g/cm ³)	at 25 °C	1.11	1.12	1.13	1.18
Liquid Density (g/cm ³)	at 25 °C	1.04	1.04	1.06	1.09
Package Volume		1 kg bottle	1 kg bottle	1 kg bottle	1 kg bottle
Layer Thickness (mm) Standard Mode		0.05	0.05	0.10	0.02
Vertical Build Speed Standard Mode (mm/hr) Draft Mode (mm/hr)		78 104	41 68	47 NA	8 NA
Tensile Strength (MPa)	ASTM D638	50	48	3.6	13.7
Tensile Modulus (MPa)	ASTM D638	2180	2120	3.6	262
Elongation at Break	ASTM D638	25%	35%	83%	12%
Elongation at Yield	ASTM D638	4%	4%	NA	NA
Flexural Strength (MPa)	ASTM D790	75	73	NA	NA
Flexural Modulus (MPa)	ASTM D790	2070	1960	NA	NA
Notched Izod Impact Strength (J/m)	ASTM D256	29	32	NA	NA
Unnotched Izod Impact Strength (J/m)	ASTM D4812	598	599	NA	NA
Heat Deflection Temperature at 0.45 MPa at 1.82 MPa	ASTM D648	59 °C 51 °C	59 °C 51 °C	NA NA	NA NA
Coefficient of Thermal Expansion (ppm/°C) < Tg > Tg	ASTM E831	93 165	96 158	NA NA	NA 143
Tear Strength (kN/m)	ASTM D624	NA	NA	11	NA
Compression Set	ASTM D395	NA	NA	0.87%	NA
Glass Transition (Tg)	DMA, E"	58 °C	55 °C	-26 °C	NA
Hardness, Shore	ASTM D2240	81D	82D	65A	68D
Water Absorption	ASTM D570	0.34%	0.37%	1.4%	1.3%
Description		High-speed, production rigid	Economical, production rigid	Design elastomer	Jewelry castable

Contact Us

www.3dsystems.com

Warranty/Disclaimer: The performance characteristics of these products may vary according to product application, operating conditions, material combined with, or with end use. 3D Systems makes no warranties of any type, express or implied, including, but not limited to, the warranties of merchantability or fitness for a particular use.